

for the physical situations, where $dT/dp \geq 0$ and $d^2T/dp^2 \leq 0$. Among melting curves, there are a few¹ with $dT/dp < 0$ and but one (cerium¹⁵) thus far with $d^2T/dp^2 \geq 0$. The thermodynamic data for the melting of copper, silver and gold (Table I) are probably more precise and extensive than those for other elements with relatively high melting points. One of the most uncertain of the data in Table I is probably the value for the thermal expansion of liquid gold,¹⁶ which is believed to be an overestimate because the values given in the same paper¹⁶ for copper and silver are higher than the presently preferred values. There do not appear to be direct measurements of any type for the compressibilities of the liquids and solids near the melting points. The present experimental results and the data collected in Table I allow, however, estimates of $(\partial\Delta V/\partial p)$ via Eqs. (1), (2), and (3).

The suggested inequalities of Eqs. (2) and (3) must be subject to empirical testing for each material considered. For copper, silver, and gold, the inequality $(\partial\Delta V/\partial T)_p > (dT/dp)\Delta C_p/T$ is satisfied beyond doubt. If it is assumed that Eqs. (2) and (3) are valid, the following lower limits for $-(\partial\Delta V/\partial p)_T$ are estimated as (in units of $\text{cm}^3/\text{g atom Mbar}$) Cu, 1.6; Ag, 2.6; Au, 1.2 at the respective zero-pressure melting points. The bounds implied for $(\partial\Delta V/\partial p)$ via Eq. (1) may be examined by writing an equation for the melting curve as an expansion about the zero-pressure melting point, viz

$$T = T_0 + p(dT/dp)_{p=0} + \frac{1}{2}p^2(d^2T/dp^2)_{p=0} + \dots \quad (4)$$

If the experimentally determined initial slopes are identified with $(dT/dp)_{p=0}$ and the deviations from linearity and/or experimental uncertainties are identified with the next term, estimates can be obtained for $(d^2T/dp^2)_{p=0}$. Thus

$$-2|\Delta T|/p^2 \lesssim (d^2T/dp^2)_{p=0}, \quad (5)$$

where the right-hand side may be estimated from Eq. (1). The upper bounds for $-(\partial\Delta V/\partial p)_T$, obtained in this way, are: Cu, 7.5; Ag, 3.9; Au, 3.4 (in units of $\text{cm}^3/\text{g atom Mbar}$).

The validity of these bounds for $(\partial\Delta V/\partial p)_T$ is difficult to assess since the estimates are based on empirical relations [Eqs. (2) and (3)] and on experimental data uncorrected for the effects of pressure on thermocouple emf. Nevertheless, knowledge of $(\partial\Delta V/\partial p)_T$ is of great importance in any understanding of the course of the melting curve beyond the explored region since this term, involving the difference in compression between liquid and solid, is probably the dominant one in the expression for the variation in

volume change with pressure, viz

$$\frac{d\Delta V}{dp} = \left(\frac{\partial\Delta V}{\partial p}\right)_T + \left(\frac{dT}{dp}\right)\left(\frac{\partial\Delta V}{\partial T}\right)_p \quad (6)$$

It is more likely that the pertinent zero-pressure data are available for estimating the variation in entropy change with pressure, viz

$$\frac{d\Delta S}{dp} = -\left(\frac{\partial\Delta V}{\partial T}\right)_p + \left(\frac{dT}{dp}\right)\frac{\Delta C_p}{T} \quad (7)$$

$d\Delta S/dp \approx 0.1 \pm 0.3$ for copper, -2 ± 1 for silver, and -1.4 ± 0.4 for gold (in units of cal/g atom Mbar). It can be readily appreciated that the standards for these types of data must be very high. Only highly precise zero-pressure determinations combined with careful high-pressure experiments can give a proper basis, beyond the accumulated uncertainty, for internally self-consistent results and for any extrapolation to higher pressures and temperatures. It is doubtful whether very many of the high-pressure, high-temperature data in the literature could meet such stringent requirements.

CONCERNING THE LINDEMANN RELATION

Most of the theoretical rationalizations of the Simon equation are based on some form of the Lindemann relation, which may be expressed here as

$$M^{1/2}V^{1/3}T^{-1/2}\vartheta = \text{"constant"}, \quad (8)$$

where M is the mass of the element, V the volume of the solid at the melting point, T the absolute melting point, and ϑ the Debye temperature. For related series of elements, the "constant" often varies by less than 10%. For copper, silver and gold, the variation in the "constant" is about in this range for the Debye temperatures¹⁷ derived from specific heat, elastic moduli, resistivity, thermal expansion and x-ray intensity measurements. For the Debye temperatures deriving from elastic-moduli data, as computed by Gschneidner,¹⁷ the variation in the "constant" is less than 2%.

It should be possible to investigate the utility of the Lindemann relation for theories of melting at high pressure if measurements allowing the derivation of Debye temperatures at high pressure were available for comparison with data for the compression and melting curve of the element. In general, there are only limited data allowing estimation of the Debye temperatures at high pressure except that, fortunately, the elastic moduli at 300°K of copper, silver, and gold have been measured by Daniels and Smith¹⁸ to 10 kbar.

¹⁵ A. Jayaraman, Phys. Rev. 137, A179 (1965).

¹⁶ W. Krause and F. Sauerwald, Z. Anorg. Allgem. Chem. 181, 347 (1929).

¹⁷ K. A. Gschneidner, Solid State Phys. 16, 275 (1964).

¹⁸ W. B. Daniels and C. S. Smith, Phys. Rev. 111, 713 (1958).